

## Divine Cork (India) Pvt. Limited

An ISO 9001:2015 Company



# RUBBERIZED CORK AUTOMOTIVE GASKETS

#### **Description:**

We provide our customers with a wide variety of die-cut Rubberized Cork Automotive Gaskets. The complete range is manufactured using high grade raw materials and advanced production methods to ensure they last for a long period of time.

### **Product Data Sheet - Dolphin Brand**

	Grade	General Purpose			Medium Oil Resistance			Good Oil Resistance			Very Good Oil Resistance			Excellent Good Oil and Heat Resistance
	Grades and Properties	RC 50A	RC 70A	RC 80A	RC 50	RC 70	RC 80	RC 50B	RC 70B	RC 80B	RC 50C	RC 70C	RC 80C	Excellent RC 70C
	Hardness IRDH	50±10	70±5	80±5	50±5	70±5	80±5	50±5	70±5	80±5	50±5	70±5	80±5	70±5
	Dimension Changes in % Max.	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5	1.5
	Tensile Strength* KPa Min.	650	900	1250	650	900	1250	700	1250	1550	1250	1550	1900	1960
	Compressibility % (At 2800 KPa)	45-60	30-45	15-30	45-60	30-45	25-40	45-60	35-50	25-35	35-45	25-35	15-25	25-35
	Recovery % Min.	80	80	80	80	80	75	80	80	80	80	80	80	80
	Compression Set % Max	90	90	90	85	85	90	80	80	80	80	80	80	80





#### Divine Cork (India) Pvt. Limited

An ISO 9001:2015 Company



#### **Chemical Test on Water Extracts**

Grade	General Purpose	Medium Oil Resistance	Good Oil Resistance	Very Good Oil Resistance	Excellent Good Oil and Heat Resistance	
(a). pH Where applicable	5.0 to 8.50	5.0 to 8.5	5.0 to 8.5	5.0 to 8.5	5.0 to 8.5	
(b). Chloride Content (As chloride ion)	0.2 % max	0.2 % max	0.2 % max	0.2 % max	0.2 % max	
(c). Sulphate Content (As sulphate ion)	0.2 % max	0.2 % max	0.2 % max	0.2 % max	0.2 % max	
Oil Immersion Test Volume Change after immersion in AsT oil No.3 for 70 hours at 100* Temp	Volume Change after immersion in AsT oil No.3 for 70 hours at 100*  Temp		25% Max.	15% Max	10% Max	
Volume Change in I.S.335 Oil			-	8%Max	6%Max	
Gasket Application Area	General Purpose	General Purpose Light Electric and General Automotive Industry	Automotive Industry and Light Electric and General Industry	Automotive Industry and Aircraft Industry	Heavy Electrical Industry; Ship Building	

<sup>\*98.0665</sup> KPa = 1KG/cm<sup>2</sup>· Grades Indicated are as per IS4253 PART II 2008.

- All materials are available in sheets measuring 610mm x 900mm, 910mm x 910mm, 1000mm x 1000mm, and 900mm x 1200mm. Rubber cork strips are available from 35 mm to 15 mm. Sheets are available in standard natural cork and black colors. Other sizes are available on request.
- Thickness: Available from 1.0 mm to 25 mm The thickness variation on sheets at any point is ±10% for thicknesses up to 6.0 mm and ±0.25 mm for thicknesses greater than 25 mm.
- Grades 70C and 80C are most preferred for the transformer and railway industries.

We also specialize in the manufacture of Rubberized Cork Automotive Gaskets in individual sizes. Though our production covers a wide range for different applications, we can also produce materials to meet your special requirements and specifications, such as granule size, tensile strength, compressibility, and oil swell.





# Divine Cork (India) Pvt. Limited

An ISO 9001:2015 Company



#### **Features:**


- Flexible
- High tensile strength
- High durability

## **Applications:**

- Transformer Industries
- Automotive and automobile Industries
- Railway Industries
- Defense Industries
- Construction Industries







W www.divinecork.com

Plot No.316/3, GIDC Estate, Nr. L & T, Road NO. 4, Ranoli - 391350, Dist. Vadodara, Gujarat, India